

# ROYCO® 49 GENERAL PURPOSE GREASE

**ROYCO® 49** is a smooth, buttery, gray-black mineral oil based grease using an inorganic gel thickener and micro-fine molybdenum disulfide that is compounded with additives to impart oxidation resistance, water washout, and both fresh and salt-water corrosion protection.

## **APPLICATIONS**

**ROYCO® 49** is intended for use in applications where severe operating conditions may include temperatures as high as 204 °C, low to moderate speeds, high loads, extreme pressure, and a salt water or high pressure steam environment. It is intended for lubrication of critical components of the shipboard aircraft catapult system, automotive, and ground support equipment. Specifically, the grease is intended for use in environments requiring normal high temperatures up to 177 °C (350 °F) or brief exposure to temperatures up to 204 °C (400 °F). It is also intended for use with systems requiring low speed, high load, salt water, and contact with high pressure steam. ROYCO® 49 should not be used in high-speed anti-friction bearings without prior performance evaluation.

#### **FEATURES AND BENEFITS**

#### **Features**

- ROYCO® 49 is composed of a high-viscosity mineral oil with a non-soap thickener and molybdenum disulfide
- Extreme-pressure additives
- Fortified with a Corrosion Resistance additive package

### **Benefits**

- Extended use at temperatures up to 177°C (350°F) and for brief periods of use at temperatures up to 204°C (400°F).
- Avoids excessive wear under shock load and low speed
- Maintains excellent grease performance in adverse weather or other water-exposure, steam and sea-water related conditions





# **APPROVALS AND SPECIFICATIONS**

**ROYCO® 49** meets all requirements and is qualified against the latest revision level of MIL-SPEC: MIL-DTL-23549D Notice 1, which supersedes MIL-G-23549C.

PROPERTIES	TEST METHOD	ROYCO® 49
Penetration, worked	ASTM D217	296
Dropping Point, °C (F)	ASTM D2265	310 (590)
Oil Separation, %, 177°C (350°F), 30 hrs	FTM 321	0.88
Evaporation, %, 177°C (350°F), 22 hrs	ASTM D2595	2.34
Load Carrying Capacity, kgf	ASTM D2596	59
Salt Spray Corrosion, galvanic corrosion	FTM 5322	Pass
Boiling Water Immersion, 10 minutes	FTM 3463	Pass
Copper Corrosion, 149°C (300°F), 24 hrs, ASTM color change	FTM 5309	1B

# **PACKAGING**

**ROYCO® 49** is available in 400 pound drums, 35 pound pails. Other package sizes may be available on special request.





This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

©2017 LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.

North America +1.833.LANXESS customer.care@lanxess.com **Europe, Middle East & Africa** +44.161.875.3800 emea.export@lanxess.com

South & Central America +55.19.3522.5083 atendimento.cliente@lanxess.com Asia Pacific +86.21.6109.6666 Orders.apac@lanxess.com

