

# ROYCO<sup>®</sup> 81MS SYNTHETIC HIGH TEMPERATURE LUBRICANT MOLYBDENUM DISULFIDE, SILICONE BASE

**ROYCO® 81MS** is a homogeneous, high-temperature semi-fluid lubricant formulated with lubricant-grade micro-fine molybdenum disulfide ( $MoS_2$ ) and thermally stable methyl phenyl polysiloxane synthetic oil. This gray-black mixture may be applied via paint brush, squirt can, or pressure applicator. The  $MoS_2$  particles of adhere and penetrate metal surfaces thereby providing lubrication and anti-seize protection even when the oil component is removed.

# APPLICATIONS

**ROYCO® 81MS** is designed for use on slow speed sliding metal on metal surfaces operating at temperatures up to 400°C (~750°F), as found in aircraft gas turbine engines. ROYCO® 81MS may also be used as an anti-seize compound on threaded parts at temperatures up to 760°C (~1400°F). STIR WELL IMMEDIATEDLY BEFORE USING.

#### FEATURES AND BENEFITS

## **Features**

- High viscosity index silicone fluid
- Micro-fine molybdenum disulfide
- High thermal/oxidative stability

# **Benefits**

- Very wide operating temperature range - outstanding high temperature performance
- Excellent film protection at high temperatures
- Protects sliding steel surfaces even under heavily-loaded conditions.
  Minimizes excessive wear, even under shock loading.
- Extended intervals between re-lubrication

## APPROVALS AND SPECIFICATIONS

**ROYCO® 81MS** meets all requirements of DOD-L-25681D Notice 2, NATO symbol S-1735.



X

#### **TYPICAL PROPERTIES**

PROPERTIES	TEST METHOD	ROYCO <sup>®</sup> 64
Base Fluid Properties		
Viscosity, cSt (mm2/sec)		
@ 100°C	ASTM D445	16
@ 40°C		71
Flash Point, °C (°F)	ASTM D92	338 (640)
Color	ASTM D1500	0.4
Molybdenum Disulfide, wt. %	SAE-AMS-M-7866	50
Materials	Specification	Conform

#### LIMITATIONS

The persistence of the molybdenum disulfide and the high penetrating properties of the synthetic base oil make this material difficult to remove from surfaces. The material may also stain yellow metals. Use of ROYCO<sup>®</sup> 81MS on antifriction bearings has not been investigated.

## PACKAGING

**ROYCO® 81MS** is available in 24 x 1.75 pound cans. Other package sizes may be available on request.



This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

©2017 LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.

North America +1.833.LANXESS customer.care@lanxess.com Europe, Middle East & Africa +44.161.875.3800 emea.export@lanxess.com South & Central America +55.19.3522.5083 atendimento.cliente@lanxess.com Asia Pacific +86.21.6109.6666 Orders.apac@lanxess.com

